

## AURO COLOURS FOR LIFE Clear lacquer, glossy No. 515

*Technical Data Sheet*

### **Type of material**

- Environment-friendly, water-dilutable transparent varnish for interior use, based on the binding agent Decovery®.
- Free of solvents and wood preservatives.
- Consistently ecological choice of raw materials.

### **Intended purpose**

- As transparent coating for wood and wood-based materials, non-rusting metals, certain plastics or tiles.
- Interior use only; apply at least two coats of approximately 0.06 to 0,09 l/m<sup>2</sup> per coat.

### **Technical properties**

- Tested according to DIN EN 71, part 3, "safe for toys" and to DIN 53160, "saliva- and perspiration-proof".
- Acc. to EN 13300: Abrasion Class 1.
- Degree of gloss approximately 50 at a measuring angle of 20°, 85 at 60° and 95 at 85°.

### **Composition**

Water, Decovery®, cellulose, surfactants made of rapeseed oil and castor oil, silicates, liquid ammonia, Benzisothiazolinon, sodium pyrithione. See the current full declaration on [www.auro.de](http://www.auro.de). Information for allergy sufferers on 0531-28141-0.

**Colour shade:** Colourless with a slight honey shade.

**Please note:** The product has a milky appearance first but dries up to a clear and transparent film. Clear varnishes produce different effects on different woods. Consequently, a test application is recommended.

### **Application method**

Brushing, rolling (synthetic or mixed-fibre brushes, fine-pore foam rollers, short-pile finishing rollers). AURO offers an assortment of high-grade tools.

The COLOURS FOR LIFE Clear lacquer No. 515 can also be applied by spraying (high pressure, mist-reduced, airmix). Tested with Wagner SF23Plus and pistol Vector Grip. Nozzle type FineFinish TT3, nozzle size 410, gun filter red. Spray pressure 100 bar.

### **Drying time in standard climate (23 °C/ 50% rel. humidity)**

Dust dry after approximately 2 hours, workable after approximately 6 hours, curing time approximately 24 hours.

**Density:** 1,02 cm<sup>3</sup>.

**Viscosity:** Approx. 30 - 60 seconds (DIN 6 mm) at 20 °C.

**Thinner:** Ready for application, can be diluted with a maximum of 10% water

### **Application rate**

0,06 – 0,09 l/m<sup>2</sup> per coat, equalling approx. 70 - 90 µm wet coat on smooth, uniformly absorbent bases. The actual application rate depends on the base, manner of processing and surface quality. Determine exact consumption on sample.

### **Cleaning of tools**

Immediately after use remove product residues from the tools by brushing out and wash with water. Remove stubborn product residues by soaking the tools for longer periods in soap solution (AURO Plant Soap No. 411\*) and wash thoroughly with water.

**Storage stability:** At 18° C in unopened original container: 24 months.

**Packaging material:** Tinplate.

### **Disposal:**

Return completely emptied containers for recycling. Only dried product residues can be disposed of as dried paint or with the household waste. Liquid residues: EWC code 080120, designation: paints, lacquers.

### **Attention**

Product code: BSW10, coating materials, water-based, low in preservatives. Use protective glasses and A2/P2 combination filter when spraying. Avoid eating, drinking and smoking while using the paint. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not allow to enter drains, waterways or soil. Observe the information on the safe handling of the product, on labelling and hazardous substances contained in the Safety Data Sheet (download from [www.auro.de/en](http://www.auro.de/en)) and on the product label.

**Hazard class:** Does not apply.

**EU VOC value** according to 2004/42/EC II A (dWb): 130 g/l (2010). Product VOC: <= 1 g/l.

# Technical recommendations for application

## AURO COLOURS FOR LIFE Clear lacquer, glossy No. 515

### 1. SUBSTRATE

**1.1 Suitable substrates:** interior wood, wood-based materials, veneered surfaces, metals e.g. textured sheets or aluminium profiles, non-rusting metals can be coated directly. Certain plastics can also be coated, especially polar plastics such as PA, PET or PVC, tiles are also possible. Preliminary tests can identify release agents or incompatibilities. Not for floors or wood that comes into contact with the soil.

**1.2 General substrate requirements:** The substrate must be clean, able to support the paint and free of releasing agents or staining substances.

### 2. COATING SYSTEM (FOR INITIAL COATING)

**2.1 Substrate preparation:** Round off edges, clean the substrate, roughen (wear a dust mask), remove dust thoroughly. For high-quality surfaces on smooth woods, first wet with sponge, allow to dry, sand finely with the grain, brush out pores, remove all dust and clean. Use only rust-free grinding agents. Wood rich in active substances and resin, tropical woods: wash with alcohol thinner and repeat fine sanding. Remove any substances that come out of the wood such as resin or resin galls; remove damaged wood; seal open wood composites. Wood based materials: seal off the edges watertight.

#### 2.2 Basic treatment

Test woods rich in ingredients and resins, e.g., larch, for drying problems by applying a test coat! If no problems occur, treat directly with AURO Clear lacquer glossy No. 515, material can be diluted with water up to max. 10%. Other woods are primed with the clear lacquer glossy no. 515 itself, diluted with up to max. 10 % water.

**2.3 Intermediate treatment:** Fill and level damaged spots with a suited filler. Apply 1 coat of AURO COLOURS FOR LIFE Clear lacquer, glossy No. 515.

**2.4 Final treatment:** Apply at least one more coat of AURO COLOURS FOR LIFE Clear lacquer, glossy No. 515. Between coats, fine sanding (220 grit or grinding pad) is recommended, depending on the substrate and surface quality. Be careful not to damage edges and remove all dust thoroughly.

### 3. COATING SYSTEM (RENOVATION)

#### 3.1 Type of surface: greyed or damaged old coatings (repair)

##### 3.1.1 Substrate preparation

Test substrates, old coatings on adhesion and compatibility. Remove non-adhering or unsuitable old coatings, e.g., greyed or heavily weathered old coats, completely, to expose the firm wood structure.

##### 3.1.2 Subsequent treatment

New coating sequence as described under item 2.

#### 3.2 Type of surface: intact old coating (maintenance)

##### 3.2.1 Substrate preparation

Clean the substrate thoroughly, roughen (wear a dust mask), remove dust.

##### 3.2.2 Basic treatment

Does not apply on intact, adhesive surfaces

##### 3.2.3. Subsequent treatment

As described under items 2.3 and 2.4.

### 4. CLEANING AND CARE

Either clean surfaces with lukewarm water only or use AURO Paint and stain cleaner No. 435\*. Do not use alkaline solutions (e.g. ammonia or soap solutions), strongly abrasive scouring or cleaning agents, microfibre etc.

### REMARKS

- Stir well before use.
- Prior to product application, check the substrate for suitability and compatibility.
- If substrate cannot be checked, then the old coat must be removed entirely right down to the bare wood or the intact primer.
- Avoid direct exposure to sunlight, moisture influences and dirt during the application and drying.
- Application temperature at least 10 °C, max. 30 °C, max. 85% rel. humidity; optimal 20-23 °C, 50-65% rel. humidity.
- Wood moisture: max. 12% in hardwood and 15% in pinewood.
- Each subsequent coat must be speedily applied in conformity with the given coating composition only after each coat has completely dried.
- Do not expose unfinished coats to prolonged loads.
- The gloss varies with the different types of wood and is diminished by wear.
- Only use sealing compounds and adhesive tapes that are compatible with the products.
- All coating work must be adapted to the object and its use.
- The Technical Guidelines No. 20 of the Federal Committee for Paints and the Protection of Objects (BFS) must be observed.

\* See respective Technical Data Sheets.

The Technical Data Sheet gives recommendations and examples of possible use. No liability or other legal responsibility can be derived. Use of the advice does not create any legal relationship. The information provided is based on our present knowledge and does not exempt the user from his personal responsibility. The respective state-of-the-art practices must be observed when implementing coating work and the required preparations. The conditions on site and the product's suitability must be checked appropriately and professionally. With publication of a new edition this technical data sheet is no longer valid. Status: 01.02.2024